

Zerust[®] Axxanol[™] Spray-G

For superior corrosion protection in a sprayable grease, use Zerust[®]/Excor[®] Axxanol[™] Spray-G. It protects in extreme conditions, such as during outdoor storage and overseas shipping.

Axxanol[™] Spray-G provides the protection of a grease in the convenience of a sprayable form. It outperforms many other rust preventative coatings, while being easier to apply and remove, saving time and costs associated with corrosion control. The product has an oily grease consistency and provides advanced corrosion protection for parts and equipment for up to 1 year outdoors and 2 years indoors.

Axxanol[™] Spray-G can be used as a light lubricant while it provides exceptional corrosion protection. The product is resistant to water and is compatible with packaging and most rubber and plastic materials. Test on a small area before use. Check with your Zerust[®]/Excor[®] representative for a corrosion management solution most effective for your metal assets.

Application Example

A large piece of machinery was coated with Axxanol[™] Spray-G before shipment overseas. It was shipped on the deck and in extreme open-air conditions. The item arrived corrosion-free to the end customer.



Benefits

Sprayable multimetal rust preventative coating

Protects in extreme outdoor conditions

Safe for paint and plastic

Non-hazardous* disposal

Removable with an alkaline cleaner

Application Type

Storage
Shipping
During Operation
May be used with Zerust[®] VCI packaging

*Non-Hazardous Disposal: Product in unopened original container prior to use is non-hazardous waste in the United States according to 40 CFR 261 (no components listed on F, K, P or U lists; not ignitable, not corrosive, not reactive and not toxic).



Technical Data

Product Information	Solvent-based corrosion inhibitor sprayable grease.	
Application	Apply via pressurized spray	
Tested on 1010 Steel panels with 20 Ra roughness	Application temperature	50 to 122°F (10 to 50°C)
	Coverage (Dry film)	211 ft ² (20 m ²) per liter* 799 ft ² (74 m ²) per gal
	Layer Thickness (Dry film)	1 mil (25 µm)
	Removability	Alkaline cleaner
	Max VOC content	40%
	Flash Point ASTM D93	177° F (80.5°C)
	Zahn Cup #3 Viscosity	13-20 secs @ 25°C
Protection Properties	Indoors	Up to 2 years
Tested at 2 mil (50 µm)	Indoors (w/ VCI Packaging)	For years
	Outdoor	Up to 1 year
	ASTM D1748 Humidity	Meets or exceeds 2500 hrs**
	ASTM B117 Salt Spray	Meets or exceeds 1500 hrs**
	Metal types	Multimetal protection
Storage Guidelines	Store in a cool (50 to 90°F / 10 to 32°C), dry place and away from sunlight in original packaging for up to 2 years from the date of shipment.	

*The 211 ft²/liter coverage data is provided only as a guide. Practical coverage value during use is affected by many factors including operator experience, surface roughness, application method, actual equipment used and application conditions. It is possible that users may obtain significantly higher or lower coverage value based on the before mentioned factors.

**ASTM B117 and D1748 data is based on 2mil DFT with portable compressed air sprayer application.

DECLARATION

This Data sheet and information it contains is considered to be accurate at the date of printing. No representation or warranty, expressed or implied is made as to the accuracy or completeness of the data and information contained in this publication. It is the User's obligation to evaluate and use products safely and within the scope advised in the data sheet and to comply with all applicable laws and regulations.

LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on validations and tests conducted by Northern Technologies International Corporation/Zerust® or its partners and are believed to be reliable, but the accuracy or completeness thereof is not guaranteed. We warrant our products will be free from defects when shipped to customer. Our obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Northern Technologies International Corporation/Zerust® or its partners or agent of the claimed defect within 3 months after shipment of product to customer. Customer shall pay all freight charges for replacement products. We shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products. And any financial claims shall be limited to the value of the products sold. Before using, user shall determine the suitability of the product for its intended use, and user assumes all risk and liability whatsoever in connection therewith. No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of the company. The foregoing warranty is exclusive and in lieu of all other warranties, express, implied or statutory, including without limitation any implied warranty of merchantability or of fitness for a particular purpose. In no case shall Northern Technologies International Corporation/Zerust® be liable for incidental or consequential damages. For full warranty and disclaimer information visit, www.zerust.com/warranty.

©2013-2021 Northern Technologies International Corporation (NTIC). All Rights Reserved. NTIC is the owner of the following trademarks: ActivPak®, Cor Tab®, EXCOR®, Flange Saver®, ICT®, Natur-VC1®, NTI®, Plastabs®, Z-CIS®, Zerion®, ZERUST®, 洁乐特, Z-PAK® and the Color "Yellow". ABRIGO®, UNICO®, and VALENO® are registered trademarks of EXCOR GmbH, a Joint Venture Partner of NTIC.

Availability

Zerust®/Excor® Axxanol™ Spray-G is sold in a ready-to-use aerosol can and in bulk pails and drums. Large volume pricing available upon request.

Part Number	Qty
350-M-00023AC	12 oz (12 cans/case)
350-M-00023PL	5 Gal*
350-M-00023DR	55 Gal*

*5 Gallon approx. 35 lbs, 55 Gallon approx. 400 lbs

Contact an Expert

Consult your local Zerust®/Excor® representative to implement an optimum corrosion prevention system for your production facility and supply chain.

Safety

- Product in unopened original container prior to use does not meet criteria for hazardous waste according to 40 CFR 261 (no components listed on F, K, P or U lists; not ignitable, not corrosive, not reactive and not toxic).

A product of:
Northern Technologies
International Corp
4201 Woodland Road
Circle Pines, MN 55014
USA

Phone. +1 763.225.6600
Fax. +1 763.225.6645
sales@zerust.com
www.zerust.com

